

BEST AVAILABLE COPY

10/510074
DT04 Rec'd PCT/PTO 30 SEP 2004

PRIORITY CLAIM


This application claims priority from International application PCT/US03/09902, having a PCT publication number of WO 03/085346 A1, which was filed on April 1, 2003, which in turn claims priority from Great Britain patent application number GB 0207642.0, which was filed on April 2, 2002. Likewise, this national stage patent application claims priority from Great Britain patent application number GB 0207642.0, which was filed on April 2, 2002.

This Request is being submitted in accordance with the "Express Mail" procedures under Rule 37 C.F.R. 1.10. Examination of this application is respectfully requested.

If the fee submitted herewith is incorrect, the Commissioner is authorized to credit any overpayment or charge any deficit to our Deposit Account No. 50-1775 and notify us of the same.

Respectfully submitted,

Date: September 30, 2004

By: 
Karrie G. Weaver
Reg. No. 43,245
Customer No. 33072
Phone: (651) 275-9836
Fax: (651) 351-2954

KGW/JAE/14648

Rec'd PCT/PTO 30 SEP 2004



W/05/1102#2



INVESTOR IN PEOPLE

10/510074

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

PRIORITY DOCUMENT
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH
RULE 17.1(a) OR (b)

REC'D 06 JUN 2003

WIPD PCT

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.


In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed

Dated 16 April 2003



The
Patent
Office

1/77

The Patent Office
Cardiff Road
Newport
Gwent NP9 1RH

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

1. Your reference 206679/PRS/VP Q5APR02 E70810W-4 002625

2. Patent application number 02 APR 2002 0207642.0
(The Patent Office will fill in this part)

3. Full name, address and postcode of the or of each applicant (underline all surnames)

08355737001

Patents ADP number (if you know it)

OMNOVA WALLCOVERING (UK) LIMITED
TONBRIDGE ROAD
EAST PECKHAM
TONBRIDGE
KENT TM12 5JX
UNITED KINGDOM

If the applicant is a corporate body, give the country/state of its incorporation

UNITED KINGDOM

4. Title of the invention WALL LINING

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

PAGE WHITE & FARRER
54 DOUGHTY STREET
LONDON
WC1N 2LS
UNITED KINGDOM

Patents ADP number (if you know it)

1255003

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country	Priority application number (if you know it)	Date of filing (day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing (day / month / year)
1	

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:
a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or
c) any named applicant is a corporate body
See note (d))

YES

WALL LINING

This invention relates to wall linings, especially wall linings that provide enhanced thermal efficiency.

Buildings' walls typically comprises a rigid walling material such as brick or plasterboard, coated with a wall lining such as wall paper and/or paint.

There is a general desire for buildings to be energy-efficient, so as to reduce the costs of heating and cooling them. In the case of buildings' walls this is normally addressed by incorporating insulating materials such as rigid foam or heat-reflective metallic sheet into the rigid element of the wall.

Materials commonly known as phase change materials have been used in textiles (for instance for military clothing), surgical bandages and protectors for electronic components. These materials exhibit a phase change at an operational or working temperature, in the course of which they absorb or emit heat. This gives them thermal regulating properties.

It has also been proposed to incorporate phase change materials into plasterboard sheet which could then be used for the rigid elements of walls. Wall boards incorporating phase-change materials have been proposed, for example, in CBS Newsletter, Fall 1997 currently available from <http://eetd.lbl.gov/cbs/newsletter/NL16/Phase.html>; and ASHRAE Transactions: Research, Volume 99, Part 2, paper #3724). These are rigid boards formed of gypsum into which phase change materials have been incorporated with the intention of enhancing the thermal energy storage capacity of buildings whose walls are formed of the boards. Although gypsum wallboard was (due to its highly porous nature) found to make an ideal supporting medium for phase change materials, the systems that have been developed suffer from a number of problems. The preferred forms of phase change materials in such wall boards have been paraffins and fatty acids. Wall boards

incorporating paraffins present severe flammability problems, and wall boards incorporating fatty acids (which are generally derived from meat by-products and vegetables) have been found to give off unacceptable levels of odours. Most significantly, although it might be convenient to use such wall boards in building a new building, to incorporate such wall boards into an existing room would mean replacing the existing walling of the room, which would be inconvenient and messy, and potentially so costly as to outweigh the energy savings that can be expected to had.

There is a need for an improved form of walling system.

According to the present invention there is provided a wall lining comprising one or more phase change materials that each exhibit a phase change at a temperature in the range from 5 to 40°C.

Preferably the wall lining is in the form of a sheet, most preferably a flexible sheet. Preferably the sheet has an adhesive layer for adhering the sheet to a wall. Alternatively the sheet could be pasted to a wall using an additional adhesive. The adhesive layer may initially be provided with a removable backing sheet on its face opposite the body of the sheet.

The mechanism of the or each phase change is preferably endothermic with increasing temperature and exothermic with reducing temperature. At atmospheric pressure, the or each phase change material preferably has a first phase stable at a temperature below the respective phase change temperature and a second phase stable above the respective phase change temperature. The change from the first to the second phase is preferably endothermic, and the change from the second to the first phase preferably exothermic. Thus the phase change material may act as a temperature buffer about the respective phase change temperature.

Preferably the or each phase change material is in the form of particles. The size of the particles is preferably in the range from 10 to 120 microns, or up to 300 microns.

Preferably each particle is encapsulated with an impermeable coating. This coating may be constituted by a structural material of a layer of the coating, or each particle may be individually encapsulated. The coating is preferably flexible.

The particles may be embedded in a layer of the wall coating. That is preferably a polymer layer. Alternatively the particles are adhered to an absorbent layer of the wall lining, for example by impregnating a paper or textile layer of the wall lining with the particles.

Preferably the wall lining comprises from 30 to 60% by weight or alternatively by volume of the phase change material(s). Amounts outside that range could also be used.

Conveniently the or at least one of the phase change materials is hydrated below the temperature at which it exhibits the phase change, and conveniently less hydrated above that temperature. At least one of the phase change materials may be a hydrated metal salt. Phase change materials employing other mechanisms could also be used.

If wall lining comprises two phase change materials, the temperatures at which they exhibit the said phase change may suitably differ by at least 1°C. This can help to broaden the effective buffering range of the wall lining.

The wall lining could be intended to form an exposed surface of a wall to which it is applied. In that case the wall lining could be provided with a cosmetic outer face, for example a printed outer face. Alternatively, the wall lining could be affixed to a wall and then decorated, for instance by painting or by applying a sheet material such as wall paper.

In the accompanying drawings:

figure 1 is a cross-section of one form of wall coating;

figure 2 is a cross-section of a wall to which the coating of figure 1 has been applied; and

figure 3 is a cross-section of another form of wall coating; and

The present invention will now be described by way of example with reference to the drawings. In the drawing, like reference numerals designate like parts.

Figure 1 shows a cross-section of one form of wall coating. The wall coating of figure 1 is a flexible sheet having a structural or body layer 1 and an adhesive layer 2 attached to the body layer and covering one major surface of the body layer. The adhesive layer is backed by a removable backing sheet 3, which protects the adhesive layer until the coating is to be applied to a wall. The body layer 1 comprises at least one phase change material, which in this instance is provided in the form of particles 4 which are embedded in the body layer 1. The phase change material exhibits an exothermic/endothermic phase change at a working temperature. As is conventional with such so-called phase change materials, the material is such that in passing through the phase change from below the working temperature to above the working temperature the material absorbs heat (endothermic) and vice versa. When the wall coating is applied to the wall 5 of a building (see figure 2) it can assist in stabilising the temperature of the building around the working temperature, and thus enhance the building's energy efficiency.

The wall coating will now be described in more detail.

The phase change material is preferably present in the wall lining in the form of particles. Figure 1 illustrates one way in which the particles may be integrated with the wall lining. In the wall lining of figure 1 the particles 4 are embedded in a polymer material that forms the matrix of the body layer 1. Figure 2 illustrates another way in which the particles may be integrated with the wall lining. In the wall lining of figure 2, the particles have been coated on to an absorbent scrim 6 by soaking the scrim with a liquid bearing the particles, and then drying the scrim so as

to leave the particles bound to the scrim. Another option would be to have the particles bound in the adhesive layer 2.

The phase change material could be incorporated in the wall lining in another way than as particles. For example, if the phase change material were in the form of a sheet then it could be laminated to the body layer 1 between the body layer and the adhesive layer 2. The phase change material could be attached to the body layer by an additional adhesive layer.

The phase change material could, for example be a hydrated metal salt such as hydrated aluminium chloride, hydrated magnesium chloride or Glauber's salt (sodium sulphate decahydrate). Alternative materials are listed in the following table.

Material	Formula	Melting range
Ca chloride hexahydrate	$\text{Ca Cl} \cdot 6\text{H}_2\text{O}$	27°C
Na sulphate decahydrate	$\text{Na}_2 \text{SO}_4 \cdot 10\text{H}_2\text{O}$	32°C
Mg chloride hexahydrate	$\text{Mg Cl}_2 \cdot 6\text{H}_2\text{O}$	117°
Na thiosulphate penta hydrate	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	48°C
Polyethylene glycol(MW >2000)	$\text{H}(\text{OCH}_2 \text{CH}_2)_n\text{OH}$	Approx 45°C
Hexadecane	$\text{C}_{16}\text{H}_{34}$	18°C
Heptadecane	$\text{C}_{17}\text{H}_{36}$	22°C
Octadecane	$\text{C}_{18}\text{H}_{38}$	28°C
Nonadecane	$\text{C}_{19}\text{H}_{40}$	32°C
Eicododecane	$\text{C}_{20} \text{H}_{42}$	36°C

Further alternatives include PEG/Celulose diacetate

To achieve the desired thermal properties, two or more phase change materials could be used in combination.

The working temperature of the phase change material – that is the temperature at which its relevant phase change occurs – should suitably be in the range from 5 to 40°C. One preferred possibility is for the working temperature to be around a desired lower temperature for a building interior, so that it can release heat as the temperature falls to that level: for that purpose the working temperature is suitably in the range from 8 to 14°C. Another preferred possibility is for the working temperature to be around a desired upper temperature for a building interior, so that it can absorb heat as the temperature rises to that level: for that purpose the working temperature is suitably in the range from 26 to 32°C, preferably between 28°C and 30°C. Another preferred possibility is for the working temperature to be around a desired ambient temperature for a building interior, so that it can moderate temperature changes in the building: for that purpose the working temperature is suitably in the range from 14 to 26°C. Broader-based effects may be achieved by using combinations of materials from one or more of these temperature ranges.

Many candidates for the phase change materials are hydrated materials, especially hydrated metal salts. In order to maintain such materials in a suitably hydrated state over the lifetime of the wall lining and also during manufacture of the wall lining it is preferred that they are encapsulated in an impermeable coating. This is illustrated in figures 1 and 3, in which the particles 4 comprise a core 4b of phase change material and an impermeable outer coating 4a. The outer coating 4a seals the core 4b so that the composition of the core does not change during use. The encapsulation should be performed below the phase change material's phase change temperature since in that range its degree of hydration will be stable. The encapsulant will typically be a hydrophobic material, and it may be difficult to fully encapsulate hydrated materials with such a material. One way in which this may be achieved is by means of the micro-encapsulation technique described in US4,675,140. That technique involves the direction of a suspension of the particles and the encapsulant on to a rotating surface. The surface centrifuges the particles surrounded by the encapsulant into air, which causes the encapsulant to cure around the particles.

Where the particles are loaded into a polymer matrix as in the coating of figure 1, the matrix itself may provide sufficient encapsulation of the particles to keep them stable during use. However, even in that embodiment it is preferred that the particles are individually encapsulated since that diminishes the possibility that the particles will deteriorate when they are loaded into the matrix during manufacture of the wall coating.

To accommodate any volume change accompanying the phase change, any encapsulant and/or matrix holding the phase change material should preferably be flexible.

The phase change material and any encapsulant should be selected to have suitable properties for safe use as a building material. For example, it should preferably be non-flammable and/or non-hazardous.

Where the phase change materials are in the form of particles, it is preferred that the particles are in the size range from 10 to 120 microns. Larger or smaller particles could also be used. Relatively small particles are preferred as they are likely to interfere less with the handling, for example cutting, of the wall lining. The loading of the particles into the wall lining is preferably in the range from 30 to 60% by weight or alternatively by volume. To assist in achieving a relatively high loading of the particles, particles of different sizes may be used. One preferred arrangement is for the matrix to include particles of two or more sets of sizes, each differing from the others in size by at least an order of magnitude. In this arrangement the particles of smaller sizes can occupy a considerable proportion of the volume between the larger particles. For example, there may be two sets of particles: one having a particle size of approximately 100 microns and one having a particle size of approximately 10 microns. The sizes of particles in each set are preferably tightly controlled to facilitate easy manufacture and to optimise filling. The particles of the largest size set preferably occupy 30 to 60% of the volume of the layer of the wall lining in which they are contained. The particles of the next

smallest size preferably occupy up to 60%, and preferably 30 to 60% of the remaining volume, and so on.

The matrix of the body layer 1 is preferably a polymer material, such as a vinyl resin. The scrim 6 could be of paper or fabric.

The wall lining is preferably in the form of a sheet, most preferably a flexible sheet, that can be applied to a wall in a similar way to conventional wall papers and vinyl wall linings. The finished sheet could be put in the form of a roll for shipping and storage, and unrolled for application to a wall. When in the form of a sheet, the outer surface of the sheet (e.g. the major surface of the body layer 1 to which the adhesive 2 is not applied, in the embodiment of figure 1) could have a decorative aspect. The outer surface could be pigmented by the application of a pigmented layer 7 to the surface, or the incorporation of pigment into the another layer of the sheet (e.g. layer 1). The outer surface could be embossed with a surface relief pattern. Alternatively, it could be intended that the wall lining should be decorated after having been installed. In that case it could have a plain exterior surface.

In summary, the wall linings of figures 1 and 3 are multilayer structures. Each embodiment comprises a layer (1,6) that forms the body of the wall lining. Phase change materials are incorporated in that layer: in one instance by being embedded in it and in the other instance by being adhered to its surface. Although it is not essential that an adhesive layer is provided, it is preferred that the wall lining comprises an adhesive layer 2 which coats one major surface of the body layer 1,6. The adhesive layer may be provided with a releasable backing layer 3 over its other major surface. One major surface of the body layer 1,6 may be provided with a decorative coating 7. If the wall lining has an adhesive layer 2, that surface is preferably the surface of the body layer to which the adhesive is not affixed.

The wall lining could include other materials intended to enhance energy efficiency by other mechanisms. For example, it could include reflective materials such as metallic fragments or metallic sheet for heat reflection.

The adhesive layer could be omitted from the coating. The coating could be fixed to a wall by an additional adhesive applied at the time of fixing, or by another means such as tacks.

Although the coating is suitable for application to walls, in practice it could be applied to other elements such as floors or ceilings.

The applicant draws attention to the fact that the present invention may include any feature or combination of features disclosed herein either implicitly or explicitly or any generalisation thereof, without limitation to the scope of any definitions set out above. In view of the foregoing description it will be evident to a person skilled in the art that various modifications may be made within the scope of the invention.

CLAIMS

1. A wall lining comprising one or more phase change materials that each exhibit a phase change at a temperature in the range from 5 to 40°C.
2. A wall lining as claimed in claim 1, wherein the wall lining is in the form of a sheet.
3. A wall lining as claimed in claim 2, wherein the sheet is a flexible sheet.
4. A wall lining as claimed in claim 3, wherein the sheet has an adhesive layer for adhering the sheet to a wall.
4. A wall lining as claimed in any preceding claim, wherein the or each phase change is endothermic with increasing temperature and exothermic with reducing temperature.
5. A wall lining as claimed in any preceding claim, wherein the or each phase change material is in the form of particles.
6. A wall lining as claimed in claim 5, wherein the size of the particles is in the range from 10 to 120 microns.
7. A wall lining as claimed in claim 5 or 6, wherein each particle is encapsulated with an impermeable coating.
8. A wall lining as claimed in claim 7, wherein the coating is flexible.
9. A wall lining as claimed in any of claims 5 to 8, wherein the particles are embedded in a layer of the wall coating.

10. A wall lining as claimed in any of claims 5 to 8, wherein the particles are adhered to an absorbent layer of the wall coating.
11. A wall lining as claimed in any preceding claim, wherein the wall lining comprises from 30 to 60% by volume of the phase change material(s).
12. A wall lining as claimed in any preceding claim, wherein the or at least one of the phase change materials is hydrated below the temperature at which it exhibits the phase change.
13. A wall lining as claimed in any preceding claim, wherein the wall lining comprises at least two phase change materials, the temperatures at which they exhibit the said phase change differing by at least 1°C.
14. A wall lining substantially as herein described with reference to the accompanying drawing.
15. A wall to which is affixed a wall lining as claimed in any preceding claim.

ABSTRACT**WALL LINING**

A wall lining comprising one or more phase change materials that each exhibit a phase change at a temperature in the range from 5 to 40°C.

Figure 1

Fig. 1




Fig. 2





Fig. 3



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☒ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.